

FEATURES

- Extended durability
- Anti-yellowing
- Hydrophobic top coat
- High density and durable coating
- Excellent antifouling performance
- Safely removable, no adhesive residual



PRODUCT STRUCTURE

Material	Aliphatic TPU
Adhesive	Pressure Sensitive Adhesive
Protection Film	50um
Top Coating Layer	12.7 um
Polyurethane	130um
Adhesive	25.4um
PET liner	50um



**The total thickness variation of the product within 5%.

Property	Test Item	Test Method	Unit	Result
Optical Property	Gloss Value	OTM-3-309		≥ 90
Physical Property	Surface Haze	ASTM D-1003	%	1.3
	Tensile Strength	D-412	psi	8000
	Elongation at break	D-412	%	>400
	Taber Abrasion	ASTM D-1044	1000g weight	≤ 3.5g
	Weathering Properties	TEST 1 *	1000 hours	No Damage
	Chemical Resistance	5% Acid 5% NAOH 100% Alcohol Gasoline	24 hours	No Damage
	Heating Resistance	80°C 2h-20°C 2h 10 cycle test		No Damage

Test 1*: QUV using UVA bulb, 4 hours 50°C UV exposure, 4 hours 60°C condensation.

**The data in this table are laboratory data for reference only.