

FEATURES

- High density and durable coating
- Excellent antifouling performance
- Yellowing and discoloration resistance
- Safely removable, no adhesive residual

PRODUCT STRUCTURE

Material	Aliphatic TPU
Adhesive	Pressure Sensitive Adhesive
Protection Film	50um
Top Coating Layer	6.5 um
Polyurethane	130um
Adhesive	25.4um
PET liner	75um

**The total thickness variation of the product within 5%.



PAINT PROTECTION FILM

GAMMA

Property	Test Item	Test Method	Unit	Result
Appearance	Rainbow/ Particle	Human-Eye	No Visible (Coated Surface)	Good
Optical Property	Gloss Value	OTM-3-309		≥ 90
Physical Property	Surface Haze	ASTM D-1003	%	1.3
	Tensile Strength	GB/T 1040	psi	≥ 2600
	Elongation at break	GB/T1040	%	≥ 320
	Taber Abrasion	ASTM D-1044	1000g weight	≤ 3.5g
	Weathering Properties	TEST 1 *	1000 hours	No Damage
	Chemical Resistance	5% Acid 5% NAOH 100% Alcohol Gasoline	24 hours	No Damage
Heating Resistance	80°C 2h-20°C 2h 10 cycle test		No Damage	

Test 1*: QUV using UVA bolb, 4 hours 50°C UV exposure, 4 hours 60°C condensation.

**The table above shows typical test results for reference only.